



# 420 Stainless

## Identification

UNS Number

• S42000

## Type Analysis

Single figures are nominal except where noted.

|                             |         |                            |                  |
|-----------------------------|---------|----------------------------|------------------|
| <b>Carbon (Minimum)</b>     | 0.15 %  | <b>Manganese (Maximum)</b> | 1.00 %           |
| <b>Phosphorus (Maximum)</b> | 0.040 % | <b>Sulfur (Maximum)</b>    | 0.030 %          |
| <b>Silicon (Maximum)</b>    | 1.00 %  | <b>Chromium</b>            | 12.00 to 14.00 % |
| <b>Iron</b>                 | Balance |                            |                  |

## General Information

### Description

CarTech 420 stainless is a hardenable 12% chrome steel with higher strength and hardness and better wear resistance than CarTech 410 stainless.

CarTech 420 stainless has been used for cutlery, surgical and dental instruments, scissors, tempered rules, tapes and straight edges, gauges, needle valves, ball check valves, gears, shafts, cams, pivots, ball bearings, magnets, etc. It also has found uses at moderately elevated temperatures-such as springs, valve parts, etc. It should not be used for springs or heavily stressed parts that must operate at sub-zero temperatures.

Plastic molders have found the unique properties of this steel of particular value. A few of the advantages provided by this steel for mold cavities have included:

Corrosion resistance  
High strength at room and moderately elevated temperatures  
Cleanness and uniformity  
Accuracy in heat treatment  
Mirror-like finishes  
Long production runs  
Easy ejection  
Chrome plating unnecessary  
Less polishing time  
Can be hobbled moderately when annealed for maximum softness

When ordering plastic mold cavities, orders should specify "CarTech 420 Mold Steel."

### Selection

There are a limited number of other alloys or variations for specific applications.

Grade 420F is characteristic of a free-machining version and TrimRite® stainless has the hardness capability of Type 420 with better corrosion resistance.

### Elevated Temperature Use

Carpenter Stainless Type 420 is not usually recommended for high temperature applications since corrosion resistance is reduced when used in the annealed condition or hardened and tempered above about 800°F (427°C). The alloy has been used at moderately elevated temperatures.

## Corrosion Resistance

Carpenter Stainless Type 420 has corrosion resistance similar to that of Type 410. It has resisted corrosion from mild atmospheres, fresh water, steam, blood, ammonia, many petroleum products and organic materials and several mild acid environments.

## 420 Stainless

For optimum corrosion resistance, surfaces must be free of scale, lubricants, foreign particles, and coatings applied for drawing and heading. After fabrication of parts, cleaning and/or passivation should be considered.

**Important Note:** The following 4-level rating scale is intended for comparative purposes only. Corrosion testing is recommended; factors which affect corrosion resistance include temperature, concentration, pH, impurities, aeration, velocity, crevices, deposits, metallurgical condition, stress, surface finish and dissimilar metal contact.

|                  |            |                   |            |
|------------------|------------|-------------------|------------|
| Nitric Acid      | Moderate   | Sulfuric Acid     | Restricted |
| Phosphoric Acid  | Restricted | Acetic Acid       | Restricted |
| Sodium Hydroxide | Moderate   | Salt Spray (NaCl) | Moderate   |
| Sour Oil/Gas     | Restricted | Humidity          | Good       |

## Properties

### Physical Properties

|                                  |                                     |
|----------------------------------|-------------------------------------|
| Specific Gravity                 | 7.69                                |
| Density                          | 0.2790 lb/in <sup>3</sup>           |
| Mean Specific Heat (32 to 212°F) | 0.1100 Btu/lb/°F                    |
| Mean CTE (32 to 212°F)           | 5.70 x 10 <sup>-6</sup> in/in/°F    |
| Thermal Conductivity (212°F)     | 173.0 BTU-in/hr/ft <sup>2</sup> /°F |
| Modulus of Elasticity (E)        | 29.0 x 10 <sup>3</sup> ksi          |
| Electrical Resistivity (70°F)    | 331.0 ohm-cir-mil/ft                |

### Typical Mechanical Properties

#### Typical Charpy V-Notch Impact Strength

1.125" (28.6 mm) round bar, hardened 1900°F (1038°C), oil quench, tempered 2 hours

| Tempering Temperature |     | Impact Strength |    | Rockwell C Hardness |
|-----------------------|-----|-----------------|----|---------------------|
| °F                    | °C  | ft-lb           | J  |                     |
| 300                   | 149 | 6               | 8  | 55                  |
| 400                   | 204 | 15              | 20 | 52                  |
| 500                   | 260 | 16              | 22 | 50½                 |
| 600                   | 316 | 14              | 19 | 50½                 |
| 700                   | 371 | 11              | 15 | 51                  |

#### Typical Elevated Temperature Mechanical Properties

Hardened 1850°F, (1010°C), tempered 1 hour 50°F (28°C) above test temperature

| Test Temperature |     | 0.2% Yield Strength |      | Ultimate Tensile Strength |      | % Elongation in 2" (50.8mm) | % Reduction of Area | Room Temp. Rockwell C Hardness After Test | Brinell Hot Hardness |
|------------------|-----|---------------------|------|---------------------------|------|-----------------------------|---------------------|-------------------------------------------|----------------------|
| °F               | °C  | ksi                 | MPa  | ksi                       | MPa  |                             |                     |                                           |                      |
| Room             |     | 184                 | 1269 | 260                       | 1793 | —                           | —                   | 51                                        | —                    |
| 400              | 204 | 227                 | 1565 | 255                       | 1758 | 8                           | 14                  | 49½                                       | 476                  |
| 600              | 316 | 225                 | 1551 | 243                       | 1675 | 9                           | 20                  | 50                                        | 401                  |
| 800              | 427 | 198                 | 1365 | 228                       | 1572 | 9                           | 19                  | 50½                                       | 401                  |
| 900              | 482 | 190                 | 1310 | 206                       | 1420 | 8                           | 17                  | 50½                                       | 370                  |
| 1000             | 538 | 96                  | 662  | 99                        | 683  | 20                          | 57                  | 36½                                       | 152                  |
| 1100             | 593 | 55                  | 379  | 65                        | 448  | 33                          | 74                  | 28½                                       | —                    |
| 1200             | 649 | 42                  | 290  | 49                        | 338  | 35                          | 82                  | 24                                        | —                    |

## 420 Stainless

### Typical Room Temperature Mechanical Properties

1" (25.4 mm) round bar

| Condition                           | 0.2% Yield Strength |      | Ultimate Tensile Strength |      | % Elongation in 2" (50.8 mm) | % Reduction of Area | Brinell Hardness |
|-------------------------------------|---------------------|------|---------------------------|------|------------------------------|---------------------|------------------|
|                                     | ksi                 | MPa  | ksi                       | MPa  |                              |                     |                  |
| Annealed<br>Hardened +<br>Tempered* | 50                  | 345  | 95                        | 655  | 25                           | 55                  | 196              |
|                                     | 215                 | 1482 | 250                       | 1724 | 8                            | 25                  | 512              |

\*1900°F (1038°C), oil quench, tempered 400°F (204°C)

### Heat Treatment

#### Annealing

For maximum softness, heat uniformly to 1550/1650°F (843/900°C) and cool slowly in furnace. Brinell hardness 179.


Intermediate or process annealing treatment-heat uniformly to 1350/1450°F (732/788°C) and furnace cool, or cool in air. Brinell hardness 196.

#### Hardening

Heat to 1850/1950°F (1010/1066°C)-soak at heat and quench in warm oil.

### Typical Longitudinal Size Change

After hardening 1900°F (1038°C) and tempering one hour



#### Tempering

To retain maximum hardness and corrosion resistance, temper at 300/400°F (149/204°C) and cool in air-Rockwell hardness approximately C 52.

For maximum corrosion resistance, Carpenter Stainless Type 420 should not be tempered over 800°F (427°C).

## 420 Stainless

### Typical Hardness

1" (25.4 mm) square, hardened 1900°F (1038°C), oil quench, tempered one hour

| Tempering Temperature |     | Hardness |            |
|-----------------------|-----|----------|------------|
| °F                    | °C  | Brinell  | Rockwell C |
| not tempered          |     | 512      | 52         |
| 300                   | 149 | 512      | 52         |
| 400                   | 204 | 512      | 52         |
| 500                   | 260 | 495      | 50         |
| 600                   | 315 | 495      | 50         |
| 700                   | 371 | 478      | 49         |
| 800                   | 427 | 478      | 49         |

For maximum corrosion resistance, Carpenter Stainless Type 420 should not be tempered over 800°F (427°C).

## Workability

### Hot Working

This steel can be readily forged, hot headed and upset.

### Forging

Preheat to 1400/1500°F (760/816°C), then heat uniformly to 2000/2200°F (1097/1204°C); forge; then cool forgings in a furnace heated to 1550°F (843°C) if possible. If not, warm dry lime or ashes can be used. If air cooled, cracking may occur. Anneal after forging; cool to room temperature before annealing. Do not forge below 1650°F (900°C)-reheat if necessary.

### Cold Working

If annealed dead soft, Carpenter Stainless Type 420 can be moderately cold formed, headed, hobbed and upset.

### Machinability

Carpenter Stainless Type 420, because of the high carbon content, machines like a high-carbon tool steel or SAE 3150 or 6150. The chips are tough and stringy. For easier machining, grinding, polishing and nongalling properties, see Carpenter Stainless Type 420F.

Following are typical feeds and speeds for Carpenter Stainless Type 420.

## 420 Stainless

### Turning—Single-Point and Box Tools

| Depth of Cut (Inches) | High Speed Tools |             |            | Carbide Tools (Inserts) |             |        |            |
|-----------------------|------------------|-------------|------------|-------------------------|-------------|--------|------------|
|                       | Tool Material    | Speed (fpm) | Feed (ipr) | Tool Material           | Speed (fpm) |        | Feed (ipr) |
|                       |                  |             |            |                         | Uncoated    | Coated |            |
| .150                  | T15              | 85          | .015       | C6                      | 375         | 500    | .015       |
| .025                  | M42              | 100         | .007       | C7                      | 450         | 600    | .007       |

### Turning—Cut-Off and Form Tools

| Tool Material    |               | Speed (fpm) | Feed (ipr)                  |       |      |       |                          |      |      |
|------------------|---------------|-------------|-----------------------------|-------|------|-------|--------------------------|------|------|
| High Speed Tools | Carbide Tools |             | Cut-Off Tool Width (inches) |       |      |       | Form Tool Width (inches) |      |      |
|                  |               |             | 1/16                        | 1/8   | 1/4  | 1/2   | 1                        | 1 ½  | 2    |
| M2               | C6            | 75          | .001                        | .0015 | .002 | .0015 | .001                     | .001 | .001 |
|                  |               | 275         | .004                        | .005  | .006 | .005  | .004                     | .003 | .003 |

### Rough Reaming

| High Speed    |             | Carbide Tools |             | Feed (ipr) Reamer Diameter (inches) |      |      |      |      |      |
|---------------|-------------|---------------|-------------|-------------------------------------|------|------|------|------|------|
| Tool Material | Speed (fpm) | Tool Material | Speed (fpm) | 1/8                                 | 1/4  | 1/2  | 1    | 1 ½  | 2    |
| T15           | 75          | C2            | 95          | .003                                | .006 | .010 | .014 | .018 | .022 |

### Drilling

| High Speed Tools |             |                                                             |      |      |      |      |      |      |      |
|------------------|-------------|-------------------------------------------------------------|------|------|------|------|------|------|------|
| Tool Material    | Speed (fpm) | Feed (inches per revolution) Nominal Hole Diameter (inches) |      |      |      |      |      |      |      |
|                  |             | 1/16                                                        | 1/8  | 1/4  | 1/2  | 3/4  | 1    | 1 ½  | 2    |
| M7,M10           | 55-65       | .001                                                        | .003 | .006 | .010 | .013 | .016 | .021 | .025 |

### Die Threading

| FPM for High Speed Tools |                |              |               |                |
|--------------------------|----------------|--------------|---------------|----------------|
| Tool Material            | 7 or less, tpi | 8 to 15, tpi | 16 to 24, tpi | 25 and up, tpi |
| M1, M2, M7, M10          | 5-15           | 10-25        | 20-35         | 25-40          |

### Milling, End-Peripheral

| Depth of Cut (Inches) | High Speed Tools |             |                                 |      |      |      | Carbide Tools |             |                                 |      |      |      |
|-----------------------|------------------|-------------|---------------------------------|------|------|------|---------------|-------------|---------------------------------|------|------|------|
|                       | Tool Material    | Speed (fpm) | Feed (ipr) Cutter Diameter (in) |      |      |      | Tool Material | Speed (fpm) | Feed (ipr) Cutter Diameter (in) |      |      |      |
|                       |                  |             | 1/4                             | 1/2  | 3/4  | 1-2  |               |             | 1/4                             | 1/2  | 3/4  | 1-2  |
| .050                  | M2, M7           | 100         | .001                            | .002 | .003 | .004 | C6            | 275         | .001                            | .002 | .004 | .006 |

### Tapping

| High Speed Tools |             |
|------------------|-------------|
| Tool Material    | Speed (fpm) |
| M1, M7, M10      | 15-40       |

### Broaching

| High Speed Tools |             |                 |
|------------------|-------------|-----------------|
| Tool Material    | Speed (fpm) | Chip Load (ipr) |
| M2, M7           | 15          | .003            |

### Additional Machinability Notes

When using carbide tools, surface speed feet/minute (sfpm) can be increased between 2 and 3 times over the high-speed suggestions. Feeds can be increased between 50 and 100%.

Figures used for all metal removal operations covered are average. On certain work, the nature of the part may require adjustment of speeds and feeds. Each job has to be developed for best production results with optimum tool life. Speeds or feeds should be increased or decreased in small steps.

### Weldability

Because it is air-hardening, Carpenter Stainless Type 420 is seldom welded. However, by preheating to 300/400°F (149/204°C) before welding, followed by a 6- to 8-hour anneal at 1350/1450°F (732/788°C) and air-cooling, satisfactory welds have been obtained.

If a filler metal is required, AWS ER 420 should be considered when the mechanical properties of the weld are important. If the mechanical properties of the weld do not have to match those of the base metal, AWS E/ER 309 should be considered.

Other Information

Applicable Specifications

- |             |             |
|-------------|-------------|
| • AMS 5621  | • ASTM A276 |
| • ASTM A314 | • ASTM A580 |
| • QQ-S-763  |             |

Forms Manufactured

- |              |                |
|--------------|----------------|
| • Bar-Flats  | • Bar-Hexagons |
| • Bar-Rounds | • Bar-Squares  |
| • Billet     | • Strip        |
| • Wire       | • Wire-Rod     |